



NR SHEETING HIGH PERFORMANCE

FEATURES

Natural rubber, para quality, translucent, with excellent mechanical properties.

APPLICATIONS

Gaskets or washers cutting and manufacturing of pieces for industrial purpose applications in contact with:

- maximum temperature 50 °C: water, water washing, alkaline and salt solutions, acids and oxidizing non oxidizing, alkali base concentration ≤50%, non food alcohol
- maximum temperature 20°C: acetones

Cutting into skirtboard and scrappers for conveyors belts, rubber sleeves, etc.

Mineral processing equipment linings, such as operating cyclones, hydrocyclones and sand treatment processes.

ADVANTAGES

- Very good mechanical properties (tensile strength, tear resistance,etc.) and at the same time, easy material to work with
- Good properties to support high mechanical strains
- Great elasticity allowing important deformations

Wrapping

Labelling

- Resistance to fine grained particles wear projection (sand, blasting)
- Good electrical properties
- Good resistance to acids, bases and salts
- Good ratio quality/price

BENEFITS

- Functionality
- ComfortService life
- Economy

MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

MEGHANICAE, I TITOICAE AND CHEMICAE I NOT ENTIES				
Measured characteristics		Standard	Value	
MECHANICAL				
Rubber compound - beige			NR	
Density			1.05 ±0.05	g/cm³
Hardness		ASTM D2240	45 ±5	Shore A
Tensile strength		ISO 37	≥16	MPa
Elongation at break		ISO 37	≥600	%
Tear resistance		ISO 34-1	≥25	N/mm
Abrasion resistance (5N)		ISO 4649	≤80	mm³
Comp	ression set after 24h at 70°C	ISO 815-1	≤30	%
TEMPERATURE				
Working temperature			-40/+85	°C
AGEING				
Δ Hardness after 70h at 70°C		ASTM D573	≤5	Shore A
Δ Tensile strength after 70h at 70°C		ASTM D573	≤-15	%
Δ Elongation at break after 70h at 70°C		ASTM D573	≤-20	%
CHEMICAL RESISTANCE				
Diluted acids and bases	Concentrated acids and bases	Ozone	Oils and hydrocarbons	
Very good	Good	Medium	Non suitable	
IDENTIFICATION				
Branding	Without.			
Packaging	Thickness ≤6mm rolled on cardboard tube Ø 80mm. Thickness >6mm in roll.			

Unless typographical error, information and figures of our technical datasheet are based on our experience and laboratory tests according to international standards. This data is intended to be used as a guideline only. Material performance depends on the conditions of use and the final application.

weight, and product code to allow product traceability.

Self-adhesive label indicating product name, dimensions, area in m2, nominal

Black polyethylene film.