



## NITRILE 70 SHEETING FOR TECHNICAL APPLICATIONS

### FEATURES

High grade 70 Shore A NBR.

### APPLICATIONS

Gaskets or washers cutting and manufacturing of pieces for general industrial purpose applications in contact with:

- mineral oils
- hydrocarbons

### ADVANTAGES

- Excellent oil and grease resistance (maximum temperature +100 °C)
- Excellent hydrocarbons resistance (aromatics content less than 30% and maximum temperature +20 °C)
- Antistatic sheeting (2.10<sup>4</sup>Ωxm) (IEC 93)
- Matte finish to guarantee a good surface finished quality and to secure an easy unrolling.

### BENEFITS

- Reliability
- Safety
- Performance

### MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

Measured characteristics		Standard	Value	
<b>MECHANICAL</b>				
Rubber compound - black			NBR	●
Density			1.30 ±0.05	g/cm <sup>3</sup>
Hardness	ASTM D2240		70 ±5	Shore A
Tensile strength	ISO 37		≥10	MPa
Elongation at break	ISO 37		≥250	%
Tear resistance	ISO 34-1		≥30	N/mm
Compression set after 24h at 70 °C	ISO 815-1		≤15	%
Compression set after 24h at 100 °C	ISO 815-1		≤20	%
<b>TEMPERATURE</b>				
Working temperature			-30/+100	°C
<b>AGEING</b>				
Δ Hardness after 72h at 100 °C	ASTM D573		≤10	Shore A
Δ Tensile strength after 72h at 100 °C	ASTM D573		±5	%
Δ Elongation at break after 72h at 100 °C	ASTM D573		≤-35	%
<b>OIL RESISTANCE</b>				
Oil IRM 901, Δ volume after 72h at 100 °C	ISO 1817		≤-16	%
Oil IRM 903, Δ volume after 72h at 100 °C	ISO 1817		±5	%
<b>CHEMICAL RESISTANCE</b>				
Diluted acids and bases	Concentrated acids and bases	Ozone	Oils and hydrocarbons	
Very good	Good	Medium	Very good	
<b>IDENTIFICATION</b>				
Branding	Without.			
Packaging	Thickness ≤6mm rolled on cardboard tube Ø 80mm. Thickness >6mm in roll.			
Wrapping	Black polyethylene film.			
Labelling	Self-adhesive label indicating product name, dimensions, area in m <sup>2</sup> , nominal weight, and product code to allow product traceability.			

Unless typographical error, information and figures of our technical datasheet are based on our experience and laboratory tests according to international standards. This data is intended to be used as a guideline only. Material performance depends on the conditions of use and the final application.